



Nelsonite
POOL AND DECK COATING

INFORMATIONAL BULLETIN #109

PROCEDURE FOR PAINTING FIBERGLASS SLIDES



INSTRUCTIONS:

- 1) Wear protective clothing and eyewear.
- 2) Remove all contaminants by washing with TSP and scrubbing with a scotch brite pad or after washing down with TSP, sand with 80 grit sandpaper.
- 3) Remove dust; solvent wipe is best.
- 4) Make sure slide is dry prior to application.
- 5) Apply two coats Dive and Slide polyurethane approx. 30 minutes apart with a 3/8 " nap roller. Before using the roller, wrap with masking tape to remove "fuzzies".
- 6) Avoid painting mid-day; late afternoon is best or morning, as long as the surface is dry.
- 7) Allow 3-4 days cure time.